



DATA SHEET

1651 East Sutter Road
Glenshaw, PA 15116-009
Phone: 412-486-4400
Fax: 412-486-6884

#10-10 Nylon Flock/Urethane Foam Composite

Description:

Unique Walco product where the wear properties and low friction surface of nylon flock are combined with the collapse resistant urethane foam. Ideal for varying gaps between offending surfaces of interior components.

Thickness Range: 1.8 mm (0.070") to 13.7 mm (0.540")

Typical Properties:

		Test Method
180° Peel Adhesion	100 oz/in.	ASTM D-3330
Tensile	80 psi	ASTM D-882
Elongation	100%	ASTM D-882
Foam Density	25-30 lb/cu. ft.	ASTM D-1667
Hardness	25 (Shore A)	ASTM D-2240
Embrittlement Temperature	-40°F (-40°C)	ASTM D-746
Recommended Service Temp.	-40°F + 200°F	

Engineering Standards:

GM: 6420M Type I, 6098M Type IV

Ford: ESBM6G17A (Flock) & WSSM2D4961-A7 (Foam)

Chrysler: MSJ2822 (Flock) & MSAY 549-4 (Foam)

WALCO MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. The Typical Properties listed above are not to be construed as specification. User is responsible for determining whether the Walco product is fit for a particular purpose and is suitable for a user's method of application. Walco assumes no obligations or liability for any advice furnished by it, or for results obtained with respect to any product(s). All such advice is given at the buyer's risk, regardless of the legal theory asserted.

Limitation of Remedies and Liability: If the Walco product is proved to be defective, THE EXCLUSIVE REMEDY, AT WALCO'S OPTION, SHALL BE TO REFUND NO MORE THAN THE PURCHASE PRICE OF OR TO REPAIR OR REPLACE THE WALCO PRODUCT PROVEN TO BE DEFECTIVE. In no event shall Walco be liable for loss or damages, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including negligence, warranty, or strict liability. No waiver, alteration, additions or modifications of the foregoing conditions shall be valid unless made in writing and manually signed by an officer of Walco Corporation.