

### #10-5 Polyester Felt

#### Description:

Extremely versatile proprietary blended polyester felt. Abrasion resistant low friction surface quiets light-duty itching and rubbing between interior trim components.  
Thickness Range: 25 mm (0.010") to 4.75 mm (0.188")

#### Typical Properties:

		Test Method
Tensile Strength	350 N/100 mm of width	ASTM D-3759
Elongation	10% Minimum	ASTM D-1000
Taber Abrasion	No wear thru to fabric backing	SEA-J 1847
Flammability	Pass	FM VSS 302
Fogging	Pass	SAE-J 1756
18° Peel Adhesion	136 oz/in.	ASTM D-3330
Tear Resistance	15.25 N	ASTM D-1004

#### Engineering Standards:

GM: 6420M Type II  
Ford: None Given  
Chrysler: None Given

WALCO MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. The Typical Properties listed above are not to be construed as specification. User is responsible for determining whether the Walco product is fit for a particular purpose and is suitable for a user's method of application. Walco assumes no obligations or liability for any advice furnished by it, or for results obtained with respect to any product(s). All such advice is given at the buyer's risk, regardless of the legal theory asserted.

Limitation of Remedies and Liability: If the Walco product is proved to be defective, THE EXCLUSIVE REMEDY, AT WALCO'S OPTION, SHALL BE TO REFUND NO MORE THAN THE PURCHASE PRICE OF OR TO REPAIR OR REPLACE THE WALCO PRODUCT PROVEN TO BE DEFECTIVE. In no event shall Walco be liable for loss or damages, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including negligence, warranty, or strict liability. No waiver, alteration, additions or modifications of the foregoing conditions shall be valid unless made in writing and manually signed by an officer of Walco Corporation.