

1651 East Sutter Road
Glenshaw, PA 15116-009
Phone: 412-486-4400
Fax: 412-486-6884

#10-6 Premium Grade Nylon Flock

Description:

Plush velvet texture. Silences itching and squeaking caused by similar/dissimilar plastics and metals.

Thickness: 1 mm

Typical Properties:

		Test Method
Tensile	30 lb. min. either direction	ASTM D-1682 GT method
Abrasion	No wear thru backing	ASTM D-4157 (15,000 cycle)
Tear Strength	4.5 lb. either direction	ASTM D-2262
Flammability	Pass	MVSS 302
Fogging	Pass	SAE-J 1756
18° Peel Adhesion	117 oz/in.	ASTM D-1000

Engineering Standards:

GM: 6420M Type IA or 1B

Ford: ESBM6G17A

Chrysler: MSJZ822

WALCO MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. The Typical Properties listed above are not to be construed as specification. User is responsible for determining whether the Walco product is fit for a particular purpose and is suitable for a user's method of application. Walco assumes no obligations or liability for any advice furnished by it, or for results obtained with respect to any product(s). All such advice is given at the buyer's risk, regardless of the legal theory asserted.

Limitation of Remedies and Liability: If the Walco product is proved to be defective, THE EXCLUSIVE REMEDY, AT WALCO'S OPTION, SHALL BE TO REFUND NO MORE THAN THE PURCHASE PRICE OF OR TO REPAIR OR REPLACE THE WALCO PRODUCT PROVEN TO BE DEFECTIVE. In no event shall Walco be liable for loss or damages, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including negligence, warranty, or strict liability. No waiver, alteration, additions or modifications of the foregoing conditions shall be valid unless made in writing and manually signed by an officer of Walco Corporation.