

10-12 Neoprene Sponge

Description:

Neoprene sponge combines the best qualities of rubber elastomers which creates an all-purpose closed cell material that can be used in many applications. This material is resistant to ozone, sunlight, and oxidation. Very good abrasion, flame resistance, is also soft and flexible with good impact absorption with few limitations.

Typical Properties:

Density:	7 to 11 lbs./cu.ft.
Hardness (Shore 00):	40 - 60 (Approximate)
Compression Deflection 25%:	5 to 9 psi
Tensile Strength (Typical):	50 psi
Elongation (Typical):	150%
Weather Resistance:	Fair (UV) and Good (Ozone)
Water Absorption by Weight:	5%
Temperature Range:	-70°F to 225°F
Flammability:	Pass (.098" or Thicker)

OEM Standards:

Testing may be required

Chrysler: MSAY 430 Type 2

GMW: 15473 Class 1 Type 4

Ford: WSK M2D 419 A Type 3

Rev. 1

WALCO MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. The Typical Properties listed above are not to be construed as specification. User is responsible for determining whether the Walco product is fit for a particular purpose and is suitable for a user's method of application. Walco assumes no obligations or liability for any advice furnished by it, or for results obtained with respect to any product(s). All such advice is given at the buyer's risk, regardless of the legal theory asserted.

Limitation of Remedies and Liability: If the Walco product is proved to be defective, THE EXCLUSIVE REMEDY, AT WALCO'S OPTION, SHALL BE TO REFUND NO MORE THAN THE PURCHASE PRICE OF OR TO REPAIR OR REPLACE THE WALCO PRODUCT PROVEN TO BE DEFECTIVE. In no event shall Walco be liable for loss or damages, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including negligence, warranty, or strict liability. No waiver, alteration, additions or modifications of the foregoing conditions shall be valid unless made in writing and manually signed by an officer of Walco Corporation.