

## 10-1 Low Density Ether Foam

### Description:

Excellent compression recovery designed for light impact applications. Also available in 4 and 6 pound densities. Good choice for sound dampening, air and dust seals, and light duty rattles.

### Typical Properties:

Density:	2lbs./cu.ft. (32 Kg/m <sup>2</sup> )
Hardness (Shore 00):	40
Force to Compress 25%:	5.4 psi (37 kPa)
Compression Set 30%:	11 (% loss from original height)
Recommended Service Temp.:	-40°F to 180°F (-35°C to -90°C)

### OEM Standards:

Testing may be required

Chrysler: MSAY301A, MSAY304A & MSAY349A

GM: 2101M Type 1

GMW: 16750

Ford: WSKM4D406A

Rev. 1

WALCO MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. The Typical Properties listed above are not to be construed as specification. User is responsible for determining whether the Walco product is fit for a particular purpose and is suitable for a user's method of application. Walco assumes no obligations or liability for any advice furnished by it, or for results obtained with respect to any product(s). All such advice is given at the buyer's risk, regardless of the legal theory asserted.

Limitation of Remedies and Liability: If the Walco product is proved to be defective, THE EXCLUSIVE REMEDY, AT WALCO'S OPTION, SHALL BE TO REFUND NO MORE THAN THE PURCHASE PRICE OF OR TO REPAIR OR REPLACE THE WALCO PRODUCT PROVEN TO BE DEFECTIVE. In no event shall Walco be liable for loss or damages, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including negligence, warranty, or strict liability. No waiver, alteration, additions or modifications of the foregoing conditions shall be valid unless made in writing and manually signed by an officer of Walco Corporation.